



**LEAKSEAL®
FLEXIBLE RUBBER SEALANT**

DESCRIPTION AND USES

Rust-Oleum® LeakSeal® Flexible Rubber Sealant is an easy to use, rubberized protective utility coating designed to fill and seal leaks and cracks. It provides a water-tight, flexible seal that prevents moisture penetration, rust and corrosion. This high-build formula is great for filling large, problematic and hard-to-reach areas.

It is suitable for use on metal, aluminum, galvanized metal, PVC, concrete, masonry, asphalt roofing materials, vinyl siding and fiberglass. Not intended for water immersion.

PRODUCTS

SKU	DESCRIPTION (946 mL)
281045	Black
281046	Crystal Clear

PRODUCT APPLICATION

SURFACE PREPARATION

Remove dirt and debris from the area to be coated. If necessary, clean the area with soap and water, rinse and let dry. All surfaces must be dry at time of application.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well ventilated area indoors. Use when temperature is between 10-29°C (10-85°F) and humidity is below 85% to ensure proper drying. Do not use on objects that may exceed 93°C (200°F) surface temperature.

Stir product slowly and carefully. **DO NOT** shake the product. Apply using a stiff bristle brush, spatula or putty knife. Dip brush slowly into the can (to avoid air bubbles) and apply the product with smooth, light, even strokes. Do not over brush into areas that are beginning to dry. Best results are achieved with several light coats versus one heavy coat. Test paint in a hidden area first.

DRY & RECOAT TIMES

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures and higher humidity. Dries to the touch in 30 minutes and can be recoated between 30 minutes and 1 hour. Dries thoroughly after 24 hours.

CLEAN-UP

Clean brush and other tools with mineral spirits.



**LEAKSEAL®
FLEXIBLE RUBBER SEALANT**

PHYSICAL PROPERTIES

		LEAKSEAL BRUSH
Resin Type		Rubber / Hydrocarbon
Pigment Type		NA
Solvents		Xylene
Weight	Per Gallon	7.61 lbs.
	Per Gallon	0.92 kg
Solids	By Weight	40.0-40.5%
	By Volume	37.0-37.5%
Volatile Organic Compounds		<550 g/l (4.58 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		2-4 mils (50-100µ)
Wet Film to Achieve DFT		5.4-10.8mils (137-275µ)
Practical Coverage at Recommended DFT		37-74 sq. ft./qt.) (3.6-7.26 m²/l)
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	15-30 minutes
	Recoat	30 minutes to 1 hour
	Fully Dry	After 24 hours
Shelf Life		5 years
Flash Point		81°F (27°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.