



**RUST-OLEUM® SPECIALTY
CAMOUFLAGE SPRAYS**

DESCRIPTION AND USES

Rust-Oleum® Specialty Camouflage Sprays are designed to provide a non-reflective finish on hunting and sporting equipment. Various colours can be combined in a variety of patterns to blend with any terrain. Camouflage Sprays are suitable for use on vehicles, tree stands, decoys, blinds, boats and equipment.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (340g Aerosol)
259513	Black
259514	Khaki
259515	Earth Brown
259516	Army Green

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply Outdoors. Apply when temperature is between 10-32°C (50-90°F) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy or dusty conditions. Cover surrounding area to protect from overspray. Overspray can carry a significant distance. Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Hold can upright 30-40 cm (12-16") from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the same distance from the surface. Keep the can in motion while spraying. Apply several light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

Apply a base coat of one colour first. Then use leaves and twigs as stencils. Apply a base coat of colour. Lay the leaves and twigs randomly over the object you are painting. Spray over the items using three or more colours.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® or a commercial detergent, or other suitable cleaning method. Mould and mildew must be cleaned with a Concrobium® Cleaner. Rinse with fresh water and allow to thoroughly dry.

PRODUCT APPLICATION – cont'd

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated coatings. Use a Zinsser® Primer for sound rusted or clean metal before application of a finish coat.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard or glossy surfaces should be scarified by sanding with GATOR® sanding products, to create a surface profile.

DRY & RECOAT

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and can be recoated within 1 hour or after 24 hours. Fully dry in 24 hours. NOTE: On plastic, maximum paint adhesion and durability is achieved in 5-7 days.

CLEAN-UP

Wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

<p>• TRUSTED QUALITY SINCE 1921 •</p> <p>RUST-OLEUM®</p> <p>SPECIALTY</p>	<p>TECHNICAL DATA</p> <p style="text-align: right;">SPC-02</p> <p style="text-align: center;">RUST-OLEUM® SPECIALTY CAMOUFLAGE SPRAYS</p>
--	--

PHYSICAL PROPERTIES

		SPECIALTY CAMOUFLAGE SPRAYS
Resin Type		Acrylic Modified Alkyd
Pigment Type		Varies with colour
Solvents		Acetone, Toluene, Xylene
MIR		0.80 Max
Fill Weight		340g (12oz)
Practical Coverage at Recommended DFT (assume 15% material loss)		Approximately 0.55 – 0.65 m ² / can (6-7 sq. ft./can)
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		93°C (200°F)
Shelf Life		5 years
Flash Point		-104°C (-156°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.