



**RUST-OLEUM® SPECIALTY  
TUB & TILE AEROSOL**

**DESCRIPTION AND USES**

Rust-Oleum® Specialty Tub & Tile Aerosol is a one-step acrylic epoxy spray paint designed to provide excellent adhesion, durability and colour retention in high moisture areas. This smooth, glossy waterproof finish is suitable for use on tiles, sinks and tubs.

**Note: Proper surface cleaning and preparation are critical to a smooth, lasting finish. Follow all directions carefully and completely.**

**PRODUCTS**

SKU	DESCRIPTION (aerosol)
280615	White
287317	Bone

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Use in a well ventilated area when air and surface temperatures are between 10-32°C (50-90°F) and humidity is below 80% to ensure proper drying. This product is not for use on galvanized metal or other metal surface.

**SURFACE PREPARATION**

Remove metal drains and hardware. Remove loose paint and rust with a wire brush or GATOR® sandpaper. Repair chips and cracks with a patching compound similar to Liquid Steel®. Remove any mildew with Concrobium® Mold Control and rinse thoroughly. Scrub dirty or stained surfaces with Krud Kutter® Mould and Mildew Stain Remover®. Rinse with fresh water and allow to thoroughly dry. Remove all Caulk. Wipe area clean. Prepare surface with a GATOR® abrasive sponge and Krud Kutter® Calcium, Lime & Rust Remover, rinse and repeat if necessary. Sand entire surface with #400/#600 grit wet/dry GATOR® sandpaper. Vacuum or rinse away any residue. Wipe surface with a tack cloth immediately before painting to remove dust. Always test product in a small, hidden area before painting.

**PRODUCT APPLICATION – cont'd**

**APPLICATION**

Open any windows and/or use fans to properly ventilate the area. Shake can vigorously for one minute after the mixing ball begins to rattle. Shake often during use. Hold can 25-40cm (10-16") from the surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2-3 light coats, spraying horizontally and vertically. **Do not use near open flame.**

**DRY & RECOAT**

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 15 minutes, to handle in 1 hour, and can be recoated at anytime. It is fully cured in 3 days.

**CLEAN-UP**

Wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	<b>TECHNICAL DATA</b>	<b>SPC-40</b>
<small>• TRUSTED QUALITY SINCE 1921 •</small> <b>RUST-OLEUM®</b> SPECIALTY	<b>RUST-OLEUM® SPECIALTY</b> <b>TUB &amp; TILE AEROSOL</b>	

**PHYSICAL PROPERTIES**

		TUB & TILE AEROSOL
<b>Resin Type</b>		Acrylic Epoxy
<b>Pigment Type</b>		Titanium Dioxide, Calcium Carbonate
<b>Solvents</b>		Acetone, Toluene, Xylene, PM Acetate
<b>MIR</b>		0.95 Max
<b>Fill Weight</b>		340g (12 oz)
<b>Practical Coverage at Recommended DFT (assume 15% material loss)</b>		Approximately 0.93-1.40 m <sup>2</sup> /can (10-15 sq.ft./can)
<b>Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity</b>	<b>Touch</b>	15 minutes
	<b>Fully Dry</b>	1 hour
	<b>Recoat</b>	Anytime
<b>Dry Heat Resistance</b>		93°C (200°F)
<b>Shelf Life</b>		2 years
<b>Flash Point</b>		-104°C (-156°F)
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.