



OUTDOOR METALLIC SPRAYS

DESCRIPTION AND USES

Rust-Oleum® Outdoor Metallic Sprays are designed to provide a durable protective coating with excellent resistance to rust, and excellent resistance to abrasion, fading, chipping and dulling. These sprays apply easily, provide excellent coverage and dry fast to a tough, attractive finish. Rust-Oleum Outdoor Metallic Sprays are ideal for ferrous, non-ferrous metal and wood surfaces. It features a comfort tip with a wider finger pad to reduce fatigue caused by continuous spraying, and an any-angle tip, which allows you to spray at any angle. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (312g)
242626	Silver
242627	Antique Brass
242628	Cobalt Blue
242629	Black Knight
242690	Gold Rush
242695	Deep Purple
308639	Rose Gold

PRODUCT APPLICATION

Apply outdoors. Use when temperature is between 10-32°C (50-90°F) and humidity is below 70% to ensure proper drying. Do not use on objects that may exceed 93°C (200°F) surface temperature, or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® or a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or GATOR® sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

PRIMING

Use of a Zinsser® Primer provides added corrosion protection, superior adhesion and hiding, and is especially recommended for bare wood and metal.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 25-40cm (10-16") from surface and spray in a

PRODUCT APPLICATION – cont'd

steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 10 minutes, to handle in 30 minutes and is fully dry in 24 hours.

CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into valve opening.



OUTDOOR METALLIC SPRAYS

PHYSICAL PROPERTIES

		OUTDOOR METALLIC SPRAYS
Resin Type		Solvent Acrylic
Pigment Type		Varies with colour
Solvents		Acetone, Toluene, Xylene
MIR		1.25 Max
Fill Weight		312g (11 oz.)
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		0.37- 0.56 m ² /can (4-6 sq. ft./can)
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	10 minutes
	Handle	30 minutes
	Fully Dry	24 hours
Dry Heat Resistance		93°C (200°F)
Shelf Life		5 years
Flash Point		-104°C (-156°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.