



**TREMCLAD®
WITH TURBO SPRAY SYSTEM™**

DESCRIPTION AND USES

Tremclad® Turbo Spray System™ delivers the trusted protection of Tremclad 3x faster than traditional aerosol cans. Up to 25cm (10") wide fan spray covers the surface in fewer passes for faster project completion. The Turbo Spray System lets you achieve professional results without using spray equipment or solvents for cleanup. Projects this big require a lot of paint, so the Turbo Spray System offers an extra tall can filled with 680g (24 ounces) of Tremclad Rust Paint. Get your to do list done in minutes with this fast, fun, new application system.

Tremclad® Rust Paint Sprays are designed to provide a durable protective coating with excellent rust prevention, and excellent resistance to abrasion, fading, chipping, and dulling. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Tremclad Sprays are ideal for ferrous, non-ferrous metal and wood surfaces. It features a comfort tip with a wider finger pad to reduce fatigue caused by continuous spraying and can be used with the Comfort Spray Grip for easier completion of larger projects. Not for use on galvanized metal.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
371479	Gloss Black
371480	Gloss White

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

Apply Outdoors. Use when temperature is between 10-32°C (50-90°F) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 93°C (200°F) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter®, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or GATOR® sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Tremclad Primer provides added corrosion protection, superior adhesion and hiding and is especially recommended for bare wood and metal.

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 25-40cm (10-16") from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. It is recommended to apply a light first coat, target 50% coverage. Apply 2 or more light coats a few minutes apart.

DRY AND RECOAT TIMES

Based on 21°C (70°F) 50% relative humidity. Allow more time at cooler temperatures.

Primer: Dries to touch in 15-30 minutes, to handle in 1-2 hours and fully dry in 48 hours. Primer may be top coated immediately.


Rust Paint: Dries to the touch in 3-4 hours, to handle in 10 hours, and is fully dry in 16 hours. Apply a second coat or Clear coat within 1 hour or after 48 hours.

CLEAN UP

Wipe off tip before storing. Clean up wet paint with Xylene or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

To clear spray for future use, turn can upside down and spray until clear gas is emitted. If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other objects into the stem.

	TECHNICAL DATA	TLC-60
	TREMCLAD® WITH TURBO SPRAY SYSTEM™	

PHYSICAL PROPERTIES

		TREMCLAD RUST PAINT WITH TURBO SPRAY SYSTEM
Resin Type		Oil modified Alkyd
Pigment Type		Varies depending on colour
Solvents		Acetone, N-Butyl Acetate, Aromatic Hydrocarbons
MIR		0.95 max
Fill Weight		680g (24 oz.)
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (32-50µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		2.2 – 3.7 sq.m/can (24-40 sq. ft./can)
Dry Times at 21°C (70°F) and 50% Relative Humidity	Touch	3-5 hours
	Handle	10 hours
	Recoat	Within 1 hour or after 48 hours
Shelf Life		5 years
Flash Point		69°C (156°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.