



UNIVERSAL[®] METALLIC SPRAYS

DESCRIPTION AND USES

Universal[®] Metallic Sprays are premium all-surface paints that provides the ultimate long-lasting protection and durability. This breakthrough, rust preventive formula adheres to plastic, wood, metal, concrete, wicker, aluminum, and masonry surfaces. A comfort grip trigger eliminates finger fatigue caused by continuous spraying. Any angle spray allows you to spray even upside down.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

PRODUCTS

| SKU | DESCRIPTION (Aerosol) |
|--------|-------------------------------|
| 246447 | Pure Gold |
| 253407 | Satin Nickel |
| 253409 | Oil Rubbed Bronze |
| 253405 | Aged Copper |
| 264658 | Rustic Mist |
| 272573 | Flat Burnished Amber |
| 272574 | Flat Soft Iron |
| 272575 | Flat Antique Nickel |
| 287323 | Aged Metallic Rust |
| 287325 | Aged Metallic Weathered Steel |
| 264649 | Dark Steel |
| 264652 | Pearl Mist |
| 264656 | Carbon Mist |
| 264659 | Champagne Mist |
| 264660 | Antique Mist |
| 317197 | Copper Rose |
| 317198 | Satin Bronze |
| 317199 | Black Stainless Steel |
| 335051 | Gilded Brass |
| 336290 | Turquoise |
| 336291 | Dark Cherry |
| 336289 | Deep Navy |
| 349908 | Aged Metallic Vintage Gold |
| 349909 | Desert Rose Gold |

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter[®] or a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or GATOR[®] sandpaper. Previously coated surfaces must be sound and in good

PRODUCT APPLICATION – cont'd

condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

APPLICATION

Apply outdoors. Use when temperature is between 10-32°C (50-90°F) and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 93°C (200°F) surface temperature.

Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Prior to use, slide off the red safety clip from the trigger. Hold can upright 20-30cm (8-12") from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart. For best results, apply several light coats versus one heavy coat. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 30 minutes, to handle in 1 hour, and is fully dry in 24 hours. Recoat within 1 hour or after 48 hours.

CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.



**UNIVERSAL[®]
METALLIC SPRAYS**

PHYSICAL PROPERTIES

| | | UNIVERSAL METALLIC SPRAYS |
|---|---------------|---|
| Resin Type | | Modified Alkyd |
| Pigment Type | | Varies with colour |
| Solvents | | Acetone, Ketone blend |
| MIR | | 1.9 Max |
| Fill Weight | | 312g (11 oz.) |
| Recommended Dry Film Thickness (DFT) per Coat | | 1.0-2.0 mils (25-50µ) |
| Practical Coverage at Recommended DFT (assume 15% material loss) | | 0.9- 1.4 m ² /can (10-15 sq. ft./can) |
| Dry Times at 25°C (77°F) and 50% Relative Humidity | Touch | 30 minutes |
| | Handle | 1 hours |
| | Recoat | Within 1 hour or after 48 hours |
| Dry Heat Resistance | | 94°C (200°F) |
| Shelf Life | | 5 years |
| Flash Point | | -104°C (-156°F) |
| Safety Information | | For additional information, see SDS |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.