



ZINSSER® BULLS-EYE 1-2-3® 3X TURBO PRIMER

DESCRIPTION AND USES

Zinsser® Bulls Eye 1-2-3® Turbo is a high hiding, all purpose, primer-sealer and stain blocker. The Turbo Spray System™ will spray up to 25cm (10") wide, allowing for faster project completing making it ideal for large projects.

It blocks and seals stains caused by water, nicotine, smoke, tannin, pencil, ink, grease and felt marker and seals smokes and other odours. Use on any interior or exterior wood, concrete, drywall or non-galvanized metal. Adheres to hard-to-paint surfaces such as railings, shutters, outdoor furniture and sticks to glossy paint, glass and ceramic tile. Perfect for sealing spackle, drywall repairs and hiding dark colours.

FEATURES

- Interior / Exterior
- Smooth finish
- Blocks tough stains
- Sticks to all surfaces
- Great for high pH surfaces
- Provides a smooth surface
- Requires less sanding
- No sag, no drip formula
- 3X greater output for quick coverage.
- Professional spray equipment results without messy clean up.
- Optimized for large projects.

PRODUCTS

SKU	DESCRIPTION (737g)
384837	Bulls-Eye 1-2-3 White

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Surfaces should be clean, dry, sound and free of dust, dirt, grime, grease, oil, wax, wallpaper adhesive or any contamination that may interfere with adhesion. If unsure of cleanliness, always wash surface with Krud Kutter® Prepaint Cleaner TSP Substitute or ammonia and water solution or solvent (Do not use TSP). Remove loose paint, dirt and rust and sand surface smooth. Lightly sand exposed exterior wood with Gator® 80-100 grit sandpaper to remove loose fibers or damaged by weather and machine glaze, then wipe down the surface to remove any dust resulting from sanding.

Mask off nearby objects and areas not intended for priming. Complete any necessary surface repairs. Countersink exposed nail heads, spot prime and fill all nail holes and gouges with Zinsser® MH Ready-Patch® spackling compound or equally suitable material.

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Ensure good cross ventilation during application.

PRODUCT APPLICATION (cont.)

Wear a NIOSH approved respirator when spraying. Use when temperature is between 10-32°C (50-90°F) and humidity is below 85% to ensure proper drying. Avoid high humidity. Do not apply to surfaces that, when heated, exceed 93°C (200°F) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

Turn can upside down and continue shaking for one minute – shake occasionally during use. If the ball does not rattle, **DO NOT STRIKE CAN**; Contact Rust-Oleum. Turn the can upside down and continue shaking for one minute. Spray 20-35 cm (8"-14") from object. Depress valve completely and apply with short 'dusting' strokes. Keep the can the same distance from the surface and in motion while spraying. **Do not use near open flame.**

NOTE: The closer the can is held to the surface, the faster you should move the can while painting to avoid drips and sags.

DRY AND RECOAT TIMES

Dries in 30 minutes, based on 21°C (70°F) 50% relative humidity. Topcoat in 30 minutes with latex or oil-base paints. For best results, allow primer to cure overnight when applying strong solvent-base topcoats. Allow more time to dry at cooler temperatures or in high humidity.

CLEAN UP

To clear spray for future use, turn can upside down and spray until clear gas is emitted. Wipe tip off before storing. Clean up wet paint with Xylol or mineral spirits. Do not burn or puncture the can, even when empty.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Replace nozzle with valve opening pointed away from you. **DO NOT** stick a pin or other objects into the stem.

DISPOSAL

To dispose of empty containers and unused product, contact your local environmental regulatory agency.

LIMITATIONS

Not recommended for floors or decks or surfaces subject to immersion or prolonged contact with water. These limitations are not to be construed as all-inclusive.

REGULATORY

FUMES MAY CATCH FIRE. CONTENTS MAY BE HARMFUL MAY EXPLODE IF HEATED. Do not smoke. Do not puncture. Do not burn. Do not get in eyes or on skin or clothing. Do not breathe fumes. Keep out of reach of children. Use only in a well-ventilated area. Keep away from flames such as a pilot light, and any object that sparks, such as an electric motor. Store away from heat. Wear an organic vapour respirator and safety glasses. **FIRST AID TREATMENT:** Contains liquefied petroleum gas, acetone, hydrotreated light distillate, n-butyl acetate. If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If on clothes, remove clothes. If breathed in, move person into fresh air.



**ZINSSER® BULLS-EYE 1-2-3®
3X TURBO PRIMER**

PHYSICAL PROPERTIES

		BULLSEYE 1-2-3 WITH TURBO SPRAY SYSTEM
Resin Type		Alkyd/Solvent-Based
Pigment Type		Inorganic
Solvents		Mineral Spirits, VM&P Naptha, Acetone
MIR		0.59 max
Fill Weight		737g
Recommended Dry Film Thickness (DFT) per Coat		2.0 mils (50µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		1.9-2.2m ² /can (20-24 sq.ft./can)
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	15-30 minutes
	Handle	20 minutes
	Recoat	30 minutes
Shelf Life @ 24°C (75°F)		5 years
Flash Point		-96°C (141°F)
Storage and Handling		4°-32°C (40°-90°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.