



# EPOXYSHIELD® PREMIUM CRACK FILLER

## DESCRIPTION AND USES

EpoxyShield® Premium Crack Filler Driveway Sealer is a premium water-based asphalt material designed to produce a flexible, durable, long-lasting seal over cracks in asphalt surfaces.

## PERFORMANCE CHARACTERISTICS

- Rubberized
- Flexible
- Durable
- Pourable

## PRODUCTS

SKU	Container Size
257888	946 mL
257557	3.78 L

## PRODUCT APPLICATION

### SURFACE PREPARATION

To ensure proper adhesion, make sure the surface is clean and clear of any contaminants. Remove any loose material in cracks. Sweep or vacuum cracks before application of the Crack Filler.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Apply only when air, material, and surface temperatures are between 15-30°C (59-86°F) and the relative humidity is below 85%. Surface temperature should not exceed 38°C (100°F). Remove cap and cut nozzle to produce an opening about 6 mm (¼") in diameter. For cracks less than 12 mm (½") deep, pour the Crack Filler directly into the crack. Level with a spatula. For deeper cracks, fill with fine sand to a depth of 12 mm (½"), then apply the Crack Filler and level.

### DRY & RECOAT TIMES

Dry times are based on 21°C (70°F). Allow for longer dry times at cooler temperatures. The Crack Filler will be dry to touch in 1 hour. Allow the surface to dry for 2 hours before applying a sealer.

### COVERAGE

One 3.78 litre bottle will fill 60 m (200 feet) of cracks that are 12 mm (½") wide and 12 mm (½") deep. Coverage will vary with the length and depth of cracks.

### CLEAN UP

Wash tools and equipment with warm soap and water immediately after use. Use mineral spirits if the product has dried.



## TECHNICAL DATA

### EPOXYSHIELD® PREMIUM CRACK FILLER

#### PHYSICAL PROPERTIES

		PREMIUM CRACK FILLER
Resin Type		Asphalt
Pigment Type		Mineral
Solvents		Water
Weight	Per Liter	1.19 kg
	Per Gallon	9.9 lbs.
Solids	By Weight	61.2%
	By Volume	53.9%
Volatile Organic Compounds		20 g/l
Practical Coverage (assumes 15% material loss)		Will fill 60 m (200 feet) of cracks 13 mm (½") wide and 13 mm (½") deep
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	1 hour
	Ready to Seal	2 hours
Shelf Life		1 year
Flash Point		> 93°C (200°F)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.