



**V8400 SYSTEM 340 VOC
FOOD AND BEVERAGE ALKYD ENAMEL**

DESCRIPTION AND USES

V8400 System 340 VOC Food and Beverage Alkyd Enamels are designed for use in food processing plants and other areas where mold and mildew are a concern. This modified alkyd coating contains additives to prevent mold and mildew growth in the dried paint film. May be applied to surfaces at temperatures as low as 18°F (-8°C). Not for use on galvanized steel.

This coating complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities.

PRODUCTS

SKU (1 Gallon)	DESCRIPTION
259157	White Clean Metal Primer
259158	High Gloss Dairy White
266691	Safety Yellow

PRODUCT APPLICATION

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® Cleaner Degreaser or other suitable cleaner. Mold and mildew areas must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to dry.

STEEL: Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust, scale, and deteriorated previous coatings to obtain a sound rusted surface. For optimum corrosion resistance, abrasive blast to commercial grade SSPC-SP-6, with a blast profile of 1-2 mils (25-50µ). All weld spatter should be removed along weld seams, rough welds should be ground smooth, and all sharp edges should be ground to a smooth radius.

APPLICATION

Apply only when air and surface temperatures are between 18-100°F (-8-38°C). Surfaces must be frost-free and at least 5°F above dew point.

EQUIPMENT RECOMMENDATIONS

BRUSH: Use a good quality natural or synthetic bristle brush.

ROLLER: Use a good quality lamb's wool or synthetic fiber roller cover recommended.

AIR-ATOMIZED SPRAY

Method	Fluid Tip	Fluid Delivery	Atomized Pressure
Pressure	0.055-0.070	16 oz./min.	40-60 psi
Siphon	0.055-0.070	--	40-60 psi
HVLP	0.043-0.070	10-12 oz./min	10 psi (at tip)

PRODUCT APPLICATION (cont.)

AIRLESS SPRAY

Fluid Pressure	Fluid Tip	Filter Mesh
2,200-3,100 psi	0.013-0.017	100

THINNING

BRUSH/ROLLER: Normally not required.

AIR-ATOMIZED SPRAY: 333402 Thinner: Use up to 15% by volume.

AIRLESS SPRAY: 333402 Thinner: Normally not required. If needed use up to 5% by volume.

CLEAN-UP

333402 Thinner or 254266 Thinner.

PERFORMANCE CHARACTERISTICS

PENCIL HARDNESS

METHOD: ASTM D3363

RESULT: 5B

CONICAL FLEXIBILITY

METHOD: ASTM D522

RESULT: >33%

CYCLIC PROHESION

Rating 1-10. 10=best

METHOD: ASTM D5894, 3 cycles, 1,008 hours

RESULT: 10 per ASTM D714 for blistering

Result: 10 per ASTM D1654 for corrosion

RESULT: 9 per ASTM D610 for rusting

IMPACT RESISTANCE (direct/reverse)

METHOD: ASTM D2794

RESULT: >60 in.-lbs.

TABER ABRASION

METHOD: ASTM D4060, CS-10 wheels, 500 gram load, 1000 cycles

RESULT: 4.2 mg loss

GLOSS (60°)

METHOD: ASTM D4587

RESULT: 91% (color-white)

Refer to the Rust-Oleum Industrial Brands Catalog (Form #275585 for chemical and corrosion resistance.

ALKYD	TECHNICAL DATA	RO-89
	V8400 SYSTEM 340 VOC FOOD AND BEVERAGE ALKYD ENAMEL	

PHYSICAL PROPERTIES

		259157 WHITE CLEAN METAL PRIMER	FINISHES
Resin Type		Phenolic Alkyd	Modified Alkyd
Pigment Type		Titanium Dioxide, Zinc Oxide, Zinc Phosphate, Calcium Carbonate, Talc	Titanium Dioxide
Solvents		Aliphatic Hydrocarbons, Propylene Glycol Monomethyl Ether Acetate	Aliphatic Hydrocarbons
Weight	Per Gallon	13.4 lbs.	9.8 lbs.
	Per Liter	1.3 kg	1.0 kg
Solids*	By Weight	79.4%	58.3%
	By Volume	61.3%	47.2%
Volatile Organic Compounds*		<340 g/l (2.08 lbs./gal.)	<340 g/l (2.08 lbs./gal.)
Recommended Dry Film (DFT) Per Coat		1.5-2.5 mils (37.5-62.5µ)	1.5-2.5 mils (37.5-62.5µ)
Wet Film to Achieve DFT (unthinned material)		2.5-4.0 mils (62.5-100µ)	2.5-4.0 mils (62.5-100µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		330-550 sq. ft./gal. (8.1-13.5 m ² /l)	250-425 sq.ft./gal. (6.2-10.5 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Tack-free	30 minutes	2-4 hours
	Handle	4-5 hours	4-8 hours
	Recoat	1 hour	24 hours
Dry Heat Resistance		212°F (100°C)	
Shelf Life		5 years	
Safety Information		FLAMMABLE LIQUID AND VAPOR. HARMFUL IF INHALED. MAY AFFECT BRAIN OR NERVOUS SYSTEM CAUSING DIZZINESS, HEADACHE OR NAUSEA. CAUSES NOSE, THROAT, EYE AND SKIN IRRITATION. FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. SEE THE PRODUCT SAFETY DATA SHEET (SDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.	

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com/industrial

Form: GDH-475
Rev.: 050619