



**LEAKSEAL®
ULTIMATE WET PATCH**

DESCRIPTION AND USES

Rust-Oleum® LeakSeal® Rubberized Wet Patch is a premium quality, heavily fibered, asphalt-based, roof cement blended with penetrating oils and plasticizing agents that can be applied directly to cold, hot, wet, dry or underwater surfaces. Rubberized Wet Patch can be used to repair and restore flashings and roofing defects such as blisters, cracks and punctures. It can also be used to adhere new asphalt ply and modified bitumen membrane flashings or seal vents, shingles, skylights and chimneys. Rubberized Wet patch resists sags and spreads very easily in cold conditions.

For exterior use only.

FEATURES

- Excellent adhesion
- All weather repairs
- Heavily fibered and flexible to resist cracking
- Sag resistant

PRODUCTS

SKU	Description
322032	300 mL Ultimate Wet Patch
322050	3.78 L Ultimate Wet Patch
322022	11.4 L Ultimate Wet Patch

PRODUCT APPLICATION

SURFACE PREPARATION

All surfaces must be clean, sound and free from dirt, grease, oil, mold, algae, loose granules or gravel, loose paint, rust, excess chalk and other foreign matter which could prevent proper adhesion.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply with a trowel directly over the clean substrate at a rate of 1.1 m² per 3.78 L (12 sq ft per 1 Gallon) and approximately 38 mm (1½") thick. When making roof repairs or stripping over the top of flashing laps, perform a 3-course repair consisting of one application of Rubberized Wet Patch followed by an embedded strip of LeakSeal Universal Patching Fabric or other mesh, followed by a final application of Rubberized Wet Patch.

COVERAGE

One 3.78 L container of Rubberized Wet Patch will cover approximately 1.1 m² (12 square feet). Actual coverage will vary depending on ambient temperature and surface conditions.

DRY TIMES

Environmental or site specific conditions may require variations in cure times.

CLEAN-UP

Clean up application tools and equipment with mineral spirits.

LIMITATIONS

Not for use on coal tar membranes.

TECHNICAL DATA

LEAKSEAL® ULTIMATE WET PATCH

PHYSICAL PROPERTIES

		ULTIMATE WET PATCH
Resin Type		Asphalt
Pigment		NA
Solvents		Mineral Spirits
Weight	Per Liter	1.18 kg
	Per Gallon	9.84 lbs.
Solids	By Weight	84.1%
	By Volume	81.3%
VOC		<200 g/l
Recommended Dry Film Thickness (DFT) per Coat		100 mils
Wet Film to Achieve DFT (unthinned material)		125 mils
Practical Coverage at Recommended DFT (assumes 15% material loss)		One 3.78 L container will cover 1.1 m ² (12.2 square feet)
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Thorough Dry	Environmental or site specific conditions will vary cure times
	Full Cure	
Shelf Life		1 year
Flash Point		38°C (100°F)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.