



## TECHNICAL DATA

# VARATHANE® WEATHERED WOOD ACCELERATOR

### DESCRIPTION AND USES

Varathane® Weathered Wood Accelerator creates a weathered look on bare or untreated wood. It replicates the aging process that occurs in nature by reacting with the tannins of the wood to create a unique one-of-a-kind aged grey look. It works on all types of wood. The final look will vary on the wood type. This water-based formula is low odor.

Not for use on outdoor surfaces. For wood substrates only. Not recommended for floors.

### PRODUCTS

SKU	Description
317176	Weathered Wood -946mL

### PRODUCT APPLICATION

#### SURFACE PREPARATION

Remove any existing finishes with sandpaper or liquid stripper. Weathered Wood Accelerator works best on bare or untreated wood. Prepare bare wood by sanding in the direction of the grain with #100 grit sandpaper. Remove any dust with a clean, dry rag.

#### TESTING COLOUR

Weathered Wood Accelerator reacts differently with different types of wood. To verify the final look, test Weathered Wood Accelerator in an inconspicuous area first.

#### APPLICATION

Stir or shake material thoroughly before and occasionally during use. For best results, use at temperatures between 15°C-32°C (60°F-90°F). Apply with a synthetic bristle brush or foam brush. Allow Weathered Wood Accelerator to sit on the wood for 30 minutes to 1 hour for the final effect. Wiping away is not required. For a lighter effect, apply product and wipe away immediately or lightly sand the finish with fine grit sandpaper once it is dry. To darken, a second coat can be applied after 1 hour. To remove Weathered Wood Accelerator, apply bleach to the surface and wipe off.

#### PROTECTING THE FINAL FINISH

A topcoat should be applied for the best protection. Wait 2 hours for Weathered Wood Accelerator to dry. For surfaces such as furniture and cabinetry, a lacquer spray can be used as the topcoat. For best results, use Watco lacquer. If you choose to topcoat with a polyurethane, first seal with Watco Lacquer spray and then apply Varathane Polyurethane. Test in an inconspicuous area first. Some topcoats may continue to react with the Weathered Wood Accelerator affecting the final work.

#### COVERAGE

Up to 25m<sup>2</sup> (275 Ft<sup>2</sup>) per 946 mL.

### CLEAN UP

Soap and Water

### REGULATORY

**CAUTION:** Use only in a well ventilated area. Do not breathe vapours. May irritate eyes and skin. Do not get in eyes, on skin or clothing.

KEEP OUT OF REACH OF CHILDREN.

**FIRST AID TREATMENT:** If breathed in, move person to fresh air. If swallowed call Poison Control Centre or doctor immediately. Do not induce vomiting. If on skin, rinse well with water.

**Not for use on outdoor surfaces. For Wood Substrates Only. Not recommended for floors.**

**TECHNICAL DATA****VARATHANE® WEATHERED WOOD ACCELERATOR****PHYSICAL PROPERTIES**

		WEATHERED WOOD ACCELERATOR
<b>Resin Type</b>		Ferrous Sulfate Heptahydrate
<b>Pigment Type</b>		NA
<b>Solvents</b>		Water
<b>Weight</b>	<b>Per Gallon</b>	8.34 lbs.
	<b>Per Liter</b>	1.00 kg
<b>Solids</b>	<b>By Weight</b>	0.43%
	<b>By Volume</b>	0.23%
<b>Volatile Organic Compounds</b>		<50 g/l (0.42 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		Varies depending on wood type and porosity
<b>Wet Film to Achieve DFT (unthinned material)</b>		Varies depending on wood type and porosity
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		Up to 25m <sup>2</sup> (275 FT <sup>2</sup> ) per 946ml- depending on wood type and porosity
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	1 hour
	<b>Recoat</b>	2-4 hours
	<b>Fully Dry</b>	4 hours
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		>93°C (>200°F)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.