



**VARATHANE® TRIPLE THICK  
ONE COAT CLEAR FINISH INTERIOR**

**DESCRIPTION AND USES**

Varathane® Triple Thick One Coat Clear Finish Interior is a protective top coat that has been specifically formulated to provide excellent durability in one coat. It provides excellent protection against scratches and stains. It features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort tip reduces finger fatigue caused by continuous spraying. Recommended for all interior surfaces; including furniture, trim, cabinets and more. It is not recommended for floors or items to be used outdoors.

**PRODUCTS**

SKU	DESCRIPTION (319g Aerosol)
334445	Clear Gloss
334447	Clear Semi-Gloss
334569	Clear Satin
334573	Clear Matte

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

Surface must be clean, dry, and free from wax, grease and dust. Sand the area smooth, progressing with sandpaper 150 to 220 grit. Vacuum surface to remove dust. Wipe the surface clean with a lint-free cloth.

**REFURBISHING** – Existing finished wood may be refurbished without complete removal of previous coating. After using furniture polishes for many years, wood can absorb contaminants that interfere with Varathane Triple Thick One Coat Clear Finish Interior. The surface must be free from wax, silicones, oils or other contaminants, thoroughly cleaned and abraded before applying Triple Thick One Coat Clear Finish Interior.

**STAINING** – For best results, use Varathane Wood Stains prior to using Triple Thick One Coat Clear Finish Interior. For other stains, follow manufacturer’s directions for application and dry times. Triple Thick One Coat Clear Finish Interior directly over a thoroughly cured stain. Test a sample for product compatibility.

**PRODUCT APPLICATION (cont.)**

**SURFACE PREPARATION (cont.)**

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**APPLICATION**

Use adequate ventilation at all times. Do not apply in direct sunlight. Apply at temperatures between 13-32°C (55-90°F) and the relative humidity is below 85%. Be careful when applying over white or pastel paints or stains as discoloration may occur. Test Varathane Triple Thick One Coat Clear Finish Interior in an inconspicuous area before beginning.

Shake the can vigorously before and during use. Use a drop cloth or newspapers to protect surrounding areas from spray mist. Apply light mist coats, holding can 25-30cm (10-12”) from the surface. Move the can with a smooth sweeping motion to avoid runs and sags. For hard to reach areas, turn the can upside down to spray. Dries to the touch in 1 hour. Let dry overnight before use.

**DRY AND RECOAT**

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 1 hour. Allow 24 hours before full use.

**CLEAN UP**

Wipe off tip before storing. Clean-up wet paint with mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into the valve opening.



**VARATHANE® TRIPLE THICK  
ONE COAT CLEAR FINISH INTERIOR**

**PHYSICAL PROPERTIES**

		TRIPLE THICK ONE COAT CLEAR FINISH
<b>Resin Type</b>		Oil Modified Urethane
<b>Pigment Type</b>		NA
<b>Solvents</b>		Acetone, Mineral Spirits, VM&P Naphtha
<b>MIR</b>		0.75 Max
<b>Fill Weight</b>		319g
<b>Recommended Dry Film Thickness (DFT) Per Coat</b>		Varies depending on surface type and porosity
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		3.7-4.6 m <sup>2</sup> /can (40-50 sq.ft./can)
<b>Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity</b>	<b>Touch</b>	1 hour
	<b>Handle</b>	2 hours
	<b>Full Cure</b>	24 hours
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-96°C (-141°F)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.