

RUST-OLEUM®



## 9700 SYSTEM

## 250 VOC ACRYLIC POLYESTER URETHANE

## DESCRIPTION AND USES

The 9700 System is a two component aliphatic acrylic polyurethane finish. These finishes are ideal for interior or exterior use on properly primed surfaces in moderate to severe industrial environments.

This highly durable, high gloss enamel is designed for use in an aggressive environment. The coating has very good chemical resistance and excellent color and gloss retention making it ideal for outdoor equipment.

## PRODUCTS

## FINISHES

1-Gallon	Description
207273	Crystal Clear
207274	Safety Blue
207277	Gloss Black
207278	Silver Gray
207279	Gloss White
207280	Dark Yellow
207243	Activator

## TINT BASES

207247	Masstone Tint Base
207271	Deep Tint Base
207272	Light Tint Base

## COMPANION PRODUCTS

SKU	Description
202548	Urethane Accelerator

## PACKAGING

Standard premix colors are packaged in short filled gallon containers to allow for the addition of activator. The activator is packaged in a short filled, cone top, quart container. The combined base and activator components will yield one full gallon.

Tint bases are packaged in short filled gallon containers to allow for the addition of colorant and activator. The following tint bases are available.

**Masstone Base** – A clear tint base that can accept up to 16 ounces of colorant per gallon.

**Deep Base** – A white tint base that contains 0.8 pounds of titanium dioxide per gallon. It can accept up to 12 ounces of colorant per gallon.

**Light Base** – A white tint base that contains 1.8 pounds of titanium dioxide per gallon. It can accept up to 8 ounces of colorant per gallon. Activated tinted colors which do not use the maximum amount of colorant will yield less than a full gallon of activated material.

## COMPANION PRODUCTS

## RECOMMENDED PRIMERS

V9100 System Low VOC DTM Epoxy Mastic

## PRODUCT APPLICATION

## SURFACE PREPARATION

**ALL SURFACES:** If excessive time has elapsed since the primer was applied, remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® Original Cleaner Degreaser, commercial detergent or other suitable cleaner. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

**STEEL:** Intended for primed steel only. Use Rust-Oleum V9100 System Low VOC DTM Epoxy Mastic as a prime coat. See primer labels and technical data sheet for correct surface preparation and application procedures.

**PREVIOUSLY COATED:** Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The 9700 System finish is compatible with most coatings, but a test patch is suggested.

**GALVANIZED METAL:** New galvanized steel must be free of grease, oil, or wax surface treatments prior to coating. Solvent wiping may be required.

## MIXING

Premix base component before adding activator, then combine at a 4:1 ratio by volume and mix together.

## APPLICATION

Apply only when air and surface temperatures are between 40-100°F (5-38°C) and surface temperature is at least 5°F (3°C) above the dew point.



**EQUIPMENT RECOMMENDATION**

**BRUSH:** Use a good quality natural or synthetic bristle brush.

**ROLLER:** Use a quality 3/8" nap lamb's wool or synthetic fiber roller cover.

**AIR-ATOMIZED SPRAY:**

Method	Fluid Tip	Fluid Delivery	Atomizing Pressure
Pressure	0.055-0.070	16 oz./min	40-60 psi
Siphon	0.055-0.070	—	40-60 psi
HVLP	0.043-0.070	10-12 oz./min.	10 psi at tip

**AIRLESS SPRAY:**

Fluid Pressure	Fluid Tip	Filter Mesh
2200-3100 psi	0.013-0.017	100

**THINNING**

Not required.

**CLEAN-UP**

Xylene or MEK.

**PERFORMANCE CHARACTERISTIC**

**SYSTEM TESTED**

Primer: Rust-Oleum Industrial DTM Epoxy Mastic with the #205015 Low VOC Standard Activator

Topcoat: Rust-Oleum Industrial Low VOC Urethane

**PENCIL HARDNESS**

METHOD: ASTM D3363

RESULT: F

**CONICAL FLEXIBILITY**

METHOD: ASTM D522

RESULT: >33%

**PROHESION**

Rating 1-10, 10=best

Method: ASTM D5894, 3300 hours

Result: 10 per ASTM D714 for blistering

Result: 10 per ASTM D1654 for corrosion

Result: 10 per ASTM D610 for rusting

**IMPACT RESISTANCE (direct/reverse)**

METHOD: ASTM D2794

RESULT: >160/>160 in.-lbs.

**TABER ABRASION**

METHOD: ASTM D4060, CS-17 wheels, 1000 gram load, 1000 cycles

RESULT: 60 mg loss

**GLOSS (60°)**

METHOD: ASTM D523

RESULT: 95% (color-white)

**ACCELERATED WEATHERING (% gloss retention)**

Method: ASTM D4587, QUV Type A bulb, 2100 Hours

RESULT: 100% (color-white)

Refer to the Rust-Oleum Industrial Brands Catalog (Form #275585 for chemical and corrosion resistance.



## TECHNICAL DATA

# 9700 SYSTEM 250 VOC ACRYLIC POLYESTER URETHANE

### PHYSICAL PROPERTIES

		PREMIX COLORS	TINT BASES
<b>Resin Type</b>		Acrylic Isocyanate converted Aliphatic Polyester Urethane (ASTM Type V)	
<b>Pigment Type</b>		Varies with color	
<b>Solvents</b>		Xylene, Esters and Ketones	
<b>Weight*</b>	<b>Per Gallon</b>	8.5-10.8 lbs.	8.6-10.0 lbs.
	<b>Per Liter</b>	1.0-1.3 kg	1.0-1.2 kg
<b>Solids*</b>	<b>By Weight</b>	56.5-73.5%	64.1-70.6%
	<b>By Volume</b>	52.6-62.8%	60.3-64.0%
<b>Volatile Organic Compounds*</b>		<250 g/l (2.08 lbs./gal.)	
<b>Recommended Dry Film (DFT) Per Coat</b>		1.0-2.0 mils (25-50µ)	1.0-2.0 mils (25-50µ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		2.0-4.0 mils (50-100µ)	2.0-4.0 mils (50-100µ)
<b>Theoretical Coverage at 1 mil DFT (25µ)</b>		845-1,010 sq.ft./gal. (20.8-24.8 m <sup>2</sup> /l)	970-1,025 sq.ft./gal. (23.9-25.2 m <sup>2</sup> /l)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		360-860 sq. ft./gal. (6.4-13.8 m <sup>2</sup> /l)	410-870 sq.ft./gal. (10.1-21.4 m <sup>2</sup> /l)
<b>Mixing Ratio</b>		4:1 Base to Activator (by volume)	4:1 Base to Activator (by volume)
<b>Induction Period</b>		None required	None required
<b>Pot Life @ 70-80°F (21-27°C) and 50% Relative Humidity</b>		3-4 hours	3-4 hours
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Tack-free</b>	5-7 hours	5-7 hours
	<b>Handle</b>	7-15 hours	7-15 hours
	<b>Recoat</b>	16-24 hours	16-24 hours
<b>Force Cure</b>		1 hour at 120°F (49°C) after 10 minute flash off	
<b>Dry Heat Resistance</b>		300°F (149°C)	
<b>Shelf Life</b>		3 years for base components; 1 year for activator (open activator should be used within 2 weeks)	
<b>Safety Information</b>		For additional information, see SDS	

\*Activated material

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.