



EPOXYSHIELD®

ULTIMATE DRIVEWAY CRACK FILLER

DESCRIPTION AND USES

EpoxyShield® Ultimate Driveway Crack Sealer is formulated with rubber designed to produce a flexible, durable, long-lasting seal over cracks in asphalt surfaces.

PERFORMANCE CHARACTERISTICS

- Rubberized
- Flexible
- Durable
- Non-tracking formula

PRODUCTS

SKU	Container Size
317751	300 mL

PRODUCT APPLICATION

SURFACE PREPARATION

To ensure proper adhesion, the surface must be clean and clear of any contaminants. Remove any loose material in cracks. Sweep or vacuum cracks before application of the Crack Filler.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air, material, and surface temperatures are between 15-30°C (59-86°F) and the relative humidity is below 85%. Surface temperature should not exceed 38°C (100°F). Cut tip of the spout at an angle to the desired tip size. Puncture the "freshness seal" at the base inside the spout. Place cartridge in a standard caulking gun and apply sealant liberally with steady pressure. A putty knife may be used to force the sealant into small cracks and to smooth the surface as desired. For cracks less than 12 mm (½") deep, pour the Crack Filler directly into the crack. Level with a spatula. For deeper cracks, fill with fine sand to a depth of 12 mm (½"), then apply the Crack Filler and level.

DRY & RECOAT TIMES

Dry times are based on 21°C (70°F). Allow for longer dry times at cooler temperatures. The Ultimate Driveway Crack Filler will be dry to touch in 1 hour. Allow the surface to dry for 2 hours before applying a sealer.

COVERAGE

One 300 mL bottle will fill 1.8-2.4 m (6-8 feet) of cracks that are 12 mm (½") wide and 12 mm (½") deep. Coverage will vary with the length and depth of cracks.

CLEAN UP

Clean up immediately with soap and water after use. Use mineral spirits if the product has dried.



TECHNICAL DATA

EPOXYSHIELD® ULTIMATE DRIVEWAY CRACK FILLER

PHYSICAL PROPERTIES

		ULTIMATE DRIVEWAY CRACK FILLER
Resin Type		Asphalt
Pigment Type		Mineral
Solvents		Water
Weight	Per Liter	1.08 kg
	Per Gallon	9.4 lbs.
Solids	By Weight	79%
	By Volume	75%
Volatile Organic Compounds		20 g/l
Practical Coverage (assumes 15% material loss)		Will fill 1.8-2.4 m (6-8 feet) of cracks that are 12 mm (½") wide and 12 mm (½") deep
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	1 hour
	Ready to Seal	2 hours
Shelf Life		1 year
Flash Point		> 93°C (200°F)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.