



**PEEL COAT®
RUGGED COAT**

DESCRIPTION AND USES

Rust-Oleum® Peel Coat® Rugged Coat is a textured, removable coating that creates a rugged, exterior look and protection from scratches and road debris. This premium formula is easy to peel, safe to wash and can be applied to metal, plastic, chrome, glass and other surfaces. Peel Coat is a temporary coating that's designed to last for 6 months.

PRODUCTS

SKU	Description
328894	Rugged Coat Black
328896	Rugged Coat Sand
328895	Rugged Coat Red

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 10- 32°C (50-90°F) and humidity is below 65% to ensure proper drying. Do not apply to galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Wash the surface with a commercial detergent or soap and water prior to the application

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 35-50 cm (14-20") from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Target 50% coverage on the first coat. Apply 4 or more light coats to build desired coating thickness and ensure coats are sufficiently dried before moving to the next maximize texture. For best results, apply 1 more final coat using short burst sprays. Allow coating to dry for about 10 minutes between coats. More coats will result in a thicker coating which is easier to remove when desired. Allow the coating to cure for 24 hours before washing. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 21°C (70°F) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes and can be handled in 1 hour.

REMOVAL

The film can be peeled off once the coating has fully cured. This coating has been formulated for temporary use and is recommended to be removed within 6 months or less. A microfiber cloth or mineral spirits may assist in the removal of coating in intricate areas.

CLEAN-UP

When finished spraying, clear the spray valve by turning can upside down and pushing the button for 5 seconds. Allow wet paint to dry and once dry, peel away or clean up wet paint with mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



TECHNICAL DATA

PEEL COAT® RUGGED COAT

PHYSICAL PROPERTIES

		PEEL COAT RUGGED COAT
Resin Type		Synthetic Rubber
Pigment Type		Varies with colour
Solvents		Blend of Acetates, Aliphatic and Aromatic Hydrocarbons
MIR		1.60 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) Per Coat		0.5-1.0 mils (per coat) (12.5-25µ per coat)
Practical Coverage at Recommended DFT		0.75 m ² /can (8 sq.ft./can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	20 minutes
Dry Heat Resistance		93°C (200°F)
Shelf Life		3 years
Flash Point		-104°C (-156°F)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.